

ALKALIES	FORMULA	POLIUREA FRIA	EUROTAFF POLIUREA
Ammonium Hydroxide <20%	NH ₄ OH	R	L
Ammonium Hydroxide >20%	NH ₄ OH	L	NR
Aqueous Ammonia	H ₃ N	R	L
Calcium Hydroxide <30%	CaH ₂ O ₂	R	L
Calcium Hypochlorite <15%	CaCl ₂ O ₂	R	L
Carbon Disulfide	CS ₂	R	L
Detergents	-----	R	L
Potassium Hydroxide <20%	KOH	R	L
Soaps	-----	R	L
Sodium Bicarbonate	NaHCO ₃	R	R
Sodium Carbonate	Na ₂ CO ₃	R	L
Sodium Chlorite	NaClO ₂	NR	NR
Sodium Hydroxide <20%	NaOH	R	L
Sodium Hydroxide <50%	NaOH	L	NR
Sodium Nitrite	NaNO ₂	L	NR
Sodium Sulfate	Na ₂ O ₄ S	R	L
Trisodium Phosphate	Na ₃ O ₄ P	R	L

SALTS	FORMULA	POLIUREA FRIA	EUROTAFF POLIUREA
Calcium Bromide	CaBr ₂	R	L
Calcium Chloride	CaCl ₂	R	L
Cuprous Chloride	CuCl	R	L
Ferric Chloride	FeCl ₃	R	L
Ferric Sulfate	Fe ₂ O ₁₂ S ₃	L	L
Ferrous Chloride	Cl ₂ Fe	R	L
Lithium Bromide	BrLi	R	L
Magnesium Chloride	Cl ₂ Mg	R	L
Magnesium Sulfate	MgO ₄ S	R	L
Potassium Iodide	KI	L	NR
Potassium Monopersulfate	K ⁺ ·O-S(=O) ₂ (-OOH)	L	NR
Sodium Chloride	NaCl	R	R
Sodium Nitrate	NaNO ₂	L	L
Zinc Bromide	ZnBr ₂	R	L

BLEACH & DETERGENTS	FORMULA	POLIUREA FRIA	EUROTAFF POLIUREA
Chlorine Dioxide	ClO ₂	R	R
Clorox	ClNaO	R	L
Hydrogen Peroxide <35%	H ₂ O ₂	L	L
Phosphorous	P	R	L
Sodium Hypochlorite <18%	NaOCl	R	L
Sodium Hypochlorite >18%	NaOCl	L	L
Sodium Silicate	Na ₄ O ₄ Si	R	L

ALCOHOLS	FORMULA	POLIUREA FRIA	EUROTAFF POLIUREA
2-Propanol	C_3H_8O	L	L
Etanol	C_2H_6O	L	L
Furfuryl	$C_5H_6O_2$	NR	NR
Isopropyl	C_3H_7	L	L
Methanol	CH_3OH	L	L

ALIPHATICS	FORMULA	POLIUREA FRIA	EUROTAFF POLIUREA
Crude Oil	-----	L	L
Diesel	-----	R	L
Fuel Oil #2	-----	R	L
Fuel Oil #4	-----	R	L
Fuel Oil #6	-----	R	L
Gasoline	-----	L	L
Heptane	C_7H_{16}	R	L
Hexane	C_6H_{14}	R	L
Hydraulic Oils	-----	R	L
JP-4	-----	L	NR
JP-5	-----	R	L
Kerosene	-----	R	L
Mineral Spirits	-----	L	L
Motor Oils	-----	R	L
Naphtha	-----	L	NR
Natural Gas	-----	R	L
Octane	C_8H_{18}	R	L
Pentane	C_5H_{12}	R	L
Transformer Oils	-----	R	L

AROMATICS	FORMULA	POLIUREA FRIA	EUROTAFF POLIUREA
Benzene	C_6H_6	L	NR
Chlorobenzene	C_6H_5Cl	L	NR
Condensate	-----	L	NR
Ethylbenzene	C_8H_{10}	L	NR
ETBE	$C_6H_{14}O$	L	NR
MTBE	$C_5H_{12}O$	L	NR
Nitrobenzene	$C_6H_5NO_2$	L	NR
PAH's	$C_9H_{10}N_2O_3$	NR	NR
Phenol	C_6H_5OH	L	NR
Styrene	C_8H_8	L	NR
Toluene	C_7H_8	L	NR
Xylene	$C_{10}H_{12}$	L	NR

KETONES	FORMULA	POLIUREA FRIA	EUROTAFF POLIUREA
Acetone	C ₃ H ₆ O	NR	NR
Methyl Amyl Ketone	C ₇ H ₁₄ O	NR	NR
Methyl Ethyl Ketone	C ₄ H ₈ O	NR	NR
Methyl Isobutyl Ketone	C ₆ H ₁₂ O	NR	NR

CHLORINATED SOLVENTS	FORMULA	POLIUREA FRIA	EUROTAFF POLIUREA
1'1' Trichloroethylene	C ₂ HCl ₃	NR	NR
Carbon Tetrachloride	CCl ₄	NR	NR
Methyl Isobutyl Chloride	C ₅ H ₁₁ Cl	NR	NR
Methylene Chloride	CH ₂ Cl ₂	NR	NR
Vinyl Trichloride	CICH ₂ CHCl ₂	NR	NR

OTHER SOLUTIONS	FORMULA	POLIUREA FRIA	EUROTAFF POLIUREA
Acetaldehyde	CH ₃ CHO	NR	NR
Acrylonitrile	C ₃ H ₃ N	NR	NR
Alum	AlH ₂₄ KO ₂₀ S ₂	R	L
Aniline	C ₆ H ₅ NH ₂	NR	NR
Animal Grease & Fats	-----	R	R
Atrazine	C ₈ H ₁₄ CIN ₅	NR	NR
Coal (Low Sulfur)	C	R	R
Coal (High Sulfur)	C	R	R
Cyclohexylamine	C ₆ H ₁₁ NH ₂	NR	NR
Dextrose	C ₆ H ₁₂ O ₆	R	R
Di-Octyl Phthalate	C ₂₄ H ₃₈ O ₄	L	L
Dibutyl Maleate	C ₁₂ H ₂₀ O ₄	NR	NR
Dibutyl Phthalate	C ₁₆ H ₂₂ O ₄	NR	NR
Diethylene Glycol Butyl Ether	C ₈ H ₁₈ O ₃	L	L
Dimethylformamide	C ₃ H ₇ NO	NR	NR
Ethylene Glycol Butyl Ether	C ₆ H ₁₄ O ₂	L	L
Formaldehyde	CH ₂ O	NR	NR
Fructose	C ₆ H ₁₂ O ₆	R	R
Guar Gum	-----	R	R
Hydroquinone	C ₆ H ₄ (OH) ₂	NR	NR
Kaolin (China Clay)	-----	R	R
Methyl Acrylate	C ₄ H ₆ O ₂	L	NR
Methacrylonitrile	C ₄ H ₅ N	NR	NR
Methyl Methacrylate	C ₅ H ₈ O ₂	NR	NR
Mono-ethanolamine	C ₂ H ₇ NO	NR	NR
Morpholine	C ₄ H ₉ NO	NR	NR
Ozone <2 ppm	O ₃	L	NR
Pine-Sol	-----	NR	NR
Polyethylene (Dry)	C ₂ H ₄	R	R

OTHER SOLUTIONS	FORMULA	POLIUREA FRIA	EUROTAFF POLIUREA
Polypropylene (Dry)	C_3H_6	R	R
Polystyrene (Dry)	C_8H_8	R	R
Polytetrafluoroethane (Dry)	$(C_2F_4)_n$	R	R
Polyvinyl Chloride (Dry)	C_2H_3Cl	R	R
Potash Ore	CK_2O_3	R	R
Pulp Liquor	-----	R	L
Quaternary Amines	-----	NR	NR
Silage	-----	R	R
Silicone Fluids	-----	R	R
Skydrol	-----	L	NR
Sugar (Saturated)	-----	R	R
Sugar Syrup	$C_{12}H_{22}O_{11}$	R	R
Toluidine	-----	NR	NR
Triethyl Phosphate	$C_6H_{15}O_4P$	NR	NR
Triethanolamine	$C_6H_{15}NO_3$	NR	NR
Urea	CH_4N_2O	R	L